



Outline NBS Specification

Existing Bituminous/Paint Substrate

This document is a guide to assist in the production of tender documents only and is not project specific. A site survey is always recommended. It is the responsibility of the client to add and delete clauses as relevant to the contract. Nothing in this proposal or any other literature produced by or on behalf of Ostman Thermal is to be regarded as constituting a contract binding in law between Ostman Thermal and any customer. The only contract which Ostman Thermal will enter into is that contained in the Ostman Thermal guarantee which takes effect only when issued in writing by Ostman Thermal to the customer. Specimen guarantees are available on request.

J31. LIQUID APPLIED WATERPROOF ROOF COATINGS

To be read with Preliminaries/General conditions.

TYPE(S) OF COATING

120. WARM DECK ROOF COATING

- Substrate: Existing Roof Structure – Bituminous /Paint Finish
 - Preparation: Clean and remove debris.
- Vapour Control Layer: Not required
- Insulation: Not Required
- Insulation adhesive: Not Required
- Overlay to insulation: Not required
- Carrier membrane: Not required.
- Waterproof coating: Ostflex System
 - System manufacturer: Ostman Thermal
 - Ostflex first coat application: 1.3 - 1.5 kg/m²
 - Ostflex second coat application: 0.5 kg/m²
 - Reinforcement: Ostflex Matting (225g/m²) to general areas in first coat
 - Minimum dry film thickness: 1.55mm
 - Ostflex Topcoat system to be applied for enhanced warranty (please refer to Ostman Thermal).
 - Colour: Dark Grey (for advice regarding other colours refer to Ostman Thermal).
- Surface protection: Not required for standard application. Anti-slip finishes available for regular foot traffic.
- Accessories: Ostflex pre-formed GRP trims
- Other surfaces: For preparation and priming of any other surfaces not itemised in this outline specification please refer to Ostflex Application Manual issued by Ostflex for guidance.
- Installation: The system should only be installed by contractors in possession of a current approval certificate and applied strictly in accordance with the Ostflex Application Manual issued by Ostman Thermal.

PERFORMANCE

210. ROOF PERFORMANCE

- General: Firmly adhered, free draining and weathertight

PRODUCTS

315. TIMBER TRIMS

- Quality: Planed, free from wane, pitch pockets, decay and insect attack (except ambrosia beetle damage)
- Moisture content at time of covering (maximum): 22%

- Preservative treatment: CCA as section Z12 and British Wood Preserving and Damp-proofing Association Commodity Specification C8

330. VAPOUR CONTROL LAYER

Not Required

333. RIGID URETHANE FOAM WARM DECK ROOF INSULATION

Not required.

353. WATERPROOF COATING

- Type: Polyurethane resin
- Manufacturer: Ostman Thermal
 - Product Reference: Ostflex
- Local Reinforcements: Ostflex Mat all junctions at upstands, penetrations and outlets.
- Ostflex first coat application: 1.3 - 1.5 kg/m²
- Ostflex second coat application: 0.5 kg/m²
- Reinforcement: Ostflex Matting (225g/m²) to general areas in first coat
- Colour: Dark Grey (for advice regarding other colours please refer to Ostflex Technical).
- Minimum dry film thickness: 1.55mm
- Surface protection: Not required for standard application. Anti-slip finishes available for regular foot traffic.

355. PERIMETER TRIMS

- Type: GRP trims
- Manufacturer: Ostman Thermal
 - Product Reference: Ostflex
- Colour: Coated with waterproof coating
- Size: Variable depending upon trim type
- Lengths: 2.5m

385. SURFACE PROTECTION (ANTI-SLIP FINISHES)

- Manufacturer: Ostman Thermal
 - Product Reference: Quartz Sand (for regular foot traffic).
- Width: To be determined by contractor.
- Colour/Finish: Various colours.
- Additives: Quartz Sand anti-slip grit Coverage: Apply 3rd coat of Ostflex at a minimum coverage rate of 0.5kg/m² and whilst wet broadcast clean dried Quartz Sand (0.7 – 1.2mm) at an approximate coverage rate of 4.0kg/m². Once cured remove loose sand. Approximate finished coverage rate of sand will be 2.5kg/m² and the remaining 1.5kg may be recovered for future use.
- Surface coverage: Even and full.

EXECUTION GENERALLY

410. ADVERSE WEATHER

- Do not apply coatings:
 - If the air temperature is outside the range of 3°C – 30°C, unless otherwise permitted by the coating manufacturer.
 - In damp or cold conditions which could cause surface condensation; during frost or if there is a risk of rain.
 - In high winds (speeds > 7 m/s) unless adequate temporary windbreaks are erected adjacent to the working area.
- Unfinished areas of roof: Keep dry.

420. SUITABILITY OF SUBSTRATES

- Substrates generally:
 - Secure, clean, dry, smooth, free from frost, contaminants, loose material, voids, protrusions and organic growths.
 - Compatible with coating system.
- Preliminary work: Complete, including:
 - Formation of upstands, kerbs, box gutters, sumps, grooves, chases and expansion joints.
 - Fixing of battens, fillets and anchoring plugs / strips.
- Moisture content and stability: Must not impair integrity of roof.

NEW SUBSTRATES/VAPOUR CONTROL LAYERS/WARM DECK BALCONY INSULATION

610. FIXING TIMBER TRIMS

- Fasteners: Sherardized steel screws.
- Fixing centres (maximum): 600mm

630. LAYING VAPOUR CONTROL LAYER

- Membrane: Bonded fully to substrate / Bonded to all crowns of the profiled sheet
- Laps: Sealed using materials and method recommended by membrane manufacturer.
- Upstands, kerbs and other penetrations: Enclose edges of insulation. Lap with coatings to form a complete seal.

660. FIXING PERIMETER TRIMS

- Fasteners: 18mm large headed galvanised clout nails to BS 1210
 - Fixing: 25mm from ends at 150 mm (maximum) centres.
- Jointing:
 - Butt straps / timber battens as appropriate.
- Corner pieces: Formed on-site.

ROOFING COATING SYSTEM

720. APPLYING PRIMERS

- Coverage per coat (minimum): One coat at 4 - 6m²/Litre

- Surface coverage: Rolled / Brushed well in to ensure local or full area coverage according to type.
- Coats: Allow to dry before overcoating.

740. MOVEMENT JOINTS IN SUBSTRATE

- Debonding tape: Apply over movement joints.
- Reinforcement strip: Apply over debonding tape.
 - Bedding: Preliminary coating application.
 - Joints: Lap in length.
 - Bond: Continuous over whole surface, with no air pockets.
 - Condition at completion: Smooth.

750. PRELIMINARY LOCAL REINFORCEMENTS

- Reinforcement strip: Ostflex and Ostflex Mat to insulation board joints and all junctions at upstands, penetrations and outlets.
 - Bedding: Preliminary coating application.
 - Joints: Lap in length.
 - Bond: Continuous over whole surface, with no air pockets.
 - Condition at completion: Smooth.

760. APPLICATION OF ROOF COATINGS

- Continuity: Maintain full thickness of coatings around angles, junctions and features.
- Rainwater outlets: Form with watertight joints.
- Drainage systems: Do not allow liquid coatings to enter piped rainwater or foul systems.
- Edge trims: Apply coatings over horizontal leg of trim and into recess.

770. SKIRTINGS AND UPSTANDS

- Top edges of coatings: Where not protected by flashings, apply into chases cut to a minimum depth of 10 mm.
- Completion of chases: When coatings are fully cured, prepare chase and apply sealant as section Z22.
- Sealant: To BS EN ISO 11600
- Colour: As coating

COMPLETION

910. INSPECTION

- Coating surfaces: Check when cured for discontinuities.
 - Defective Areas: Apply another coating.

940. COMPLETION

- Roof areas: Clean.
- Outlets: Clear.
- Flashings: Dressed into place.
- Work necessary to provide a weathertight finish: Complete.
- Storage of materials on finished surface: Not permitted.
- Completed coatings: Protect against damage.



Tel: +353 (0) 1835 3558
Tel: +44 (0) 1744 747580
www.ostmanthermal.com

